

Prince & Izant Company

12999 Plaza Drive
Cleveland, Ohio 44130
T: 216-362-7000
F: 216-362-7456
princeizant.com



APA 5 TECHNICAL DATA

NOMINAL COMPOSITION	Silver	63.0% ± 1.0
	Copper	35.25% ± 0.5
	Titanium	1.75%
	Cadmium	0.001% max.
	Zinc	0.001% max.
	Phosphorus	0.002% max.
	Lead	0.002% max.
	Carbon	0.005% max.
	Other volatile elements each*	0.002% max.
	Volatile elements total	0.010% max.
Total non-volatile elements	0.01% max.	

*Elements with a vapor pressure higher than 10^{-7} torr at 932°F (such as Mg, Sb, K, Li, Ti, S, Cs, Rb, Se, Te, Sr, and Ca) are limited to 0.001% each for Grade 1 and 0.002% for Grade 2.

PHYSICAL PROPERTIES	Solidus	1435°F (780°C)
	Liquidus	1500°F (816°C)
	Recommended Brazing Temperature	1600-1650°F (871-899°C)
	Density (Troy oz/in³)	5.2
	CTE, RT-500°C ($\times 10^{-6}/^{\circ}\text{C}$)	18.5
	Electrical Conductivity ($10^6/\text{ohm}\cdot\text{m}$)	23
	Electrical Resistivity ($10^{-9} \text{ohm}\cdot\text{m}$)	44
	Thermal Conductivity (W/m·K)	180
	Yield Strength, 0.2% offset (MPa)	271
	Tensile Strength (MPa)	346
	Young's Modulus (GPa)	83
	Elongation, 2" gage length (%)	20
Knoop Hardness (KHN)	110	

USES Suitable for brazing ceramics to metals as well as other non-metallic components without the need for prior metallization of the contact surface.

BRAZING CHARACTERISTICS Suitable for use in all vacuum brazing applications as well as under partial pressure of argon gas. Brazing of active alloys under protective nitrogen atmosphere is not recommended. It is important to maintain a high purity, oxygen-free environment; any oxidation of reactive elements will limit alloy wettability across the non-metallic surface. For controlled atmosphere brazing or vacuum brazing the recommended radial joint clearance for silver-base alloys ranges between 0-0.002 in (0-0.05 mm).

PROPERTIES OF BRAZED JOINTS

The properties of a brazed joint are dependent upon the base metal, joint design and brazing technique. This alloy in particular is ductile and will exhibit exceptional corrosion resistance due to the high silver content.

SPECIFICATIONS

APA 5 conforms to: Cusil-ABA

AVAILABLE FORMS

Wire, strip, engineered preforms, specialty preforms per customer specification, powder and paste.

SAFETY INFORMATION

The operation and maintenance of brazing equipment or facility should conform to the provisions of American National Standard (ANSI) Z49.1, "Safety in Welding and Cutting."

Individuals requiring further information and Engineering Specification Documents may wish to contact the Engineering Society for Advanced Mobility, Land Sea Air and Space, The Society of Automotive Engineers <http://www.sae.org/> (SAE AMS) or The American Welding Society (AWS) <http://aws.org/>

NOTE:

DISCLAIMER

The information and recommendations contained in this publication have been provided without charge & compiled from sources believed to be reliable and to represent the best information available on the subject at the time of issue. No warranty, guarantee, or representation is made by the Prince and Izant Company, Inc. as to the absolute correctness or sufficiency of any representation contained in this and other publications; Prince and Izant Company, Inc. assumes no responsibility in connection therewith; nor can it be assumed that all acceptable safety measures are contained in this (and other publications, or that other or additional measures may not be required under particular or exceptional conditions or circumstances.